

Product Data Sheet

Product Description

A multi use, matte finish, double sided film that will release from most synthetic resin systems: epoxies, phenolic, melamines, rubber, etc. For use in hand layup, from 0 pressure to high pressure applications (1500 PSI) and temperatures to 204 °C (400 °F).

Typical Applications

Lamination of thermoset plastics, rubber and most synthetic resins. Highly versatile.

<u>Physical</u>	<u>Typical Value</u>	<u>Units</u>	<u>Test</u>
Tensile Strength MD	25,000	PSI	ASTM D 882 A
Tensile Strength TD	30,000	PSI	ASTM D 882 A
Elongation at Break MD	90	%	ASTM D 882 A
Elongation at Break TD	60	%	ASTM D 882 A
Yield Strength MD	14,000	PSI	ASTM D 882 A
Yield Strength TD	14,000	PSI	ASTM D 882 A

<u>Thermal</u>	<u>Typical Value</u>	<u>Units</u>	<u>Test</u>
Shrinkage MD (190 °C)	2.8	%	Unrestrained 5 minutes
Shrinkage TD (190 °C)	0	%	Unrestrained 5 minutes
Melt Point	260	°C	

Note

The typical values stated above apply to Accuply® 10. Accurate Plastics does not assume liability, obligation or imply guarantee with regard to the above information.