

DELTRIN® Series Black - Stock Shapes

Chemical Designation

POM-H (Polyacetal (Homopolymer))

Colour

black

Density

1.42 g/cm³

Main features

- good machinability
- high stiffness
- high fatigue strength
- high creep resistance
- good wear properties
- very good abrasion resistance

Target Industries

- automotive industry
- construction industry
- conveyor technology
- mechanical engineering
- electronics
- fixture construction
- home appliances
- gear manufacturing

Mechanical properties	condition	value	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	350,000 psi	ASTM D 638	(1) publicly sourced data
Tensile strength at yield		11,000 psi	ASTM D 638	
Elongation at break	@ 73 °F	40 %	ASTM D 638	
Flexural strength	@ 73 °F	14,000 psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	460,000 psi	ASTM D 790	
Compression strength	@ 73 °F, 1% strain	2,700 psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	14,000 psi	ASTM D 695	
Compression modulus	@ 73 °F	460,000 psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.5 ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F R Scale	120	ASTM D 785	
Coefficient of friction	Dynamic 40 psi, 50 fpm	.2	ASTM D 3702	
Wear rate	40 psi, 50 fpm	55*10 ⁻¹⁰ in ³ -min/ft-lbs-hr	ASTM D 3702	1)
Thermal properties	condition	value	test method	comment
Melting temperature		347 °F	ASTM D 2133	1) (1) Injection molded sample (2) Resin data
Deflection temperature	@ 1.80 MPa	208 °F	ISO-R 75 Method A	2)
Service temperature	Intermittent	300 °F	-	
Service temperature	Long Term	185 °F	-	
Other properties	condition	value	test method	comment
Moisture absorption	@ saturation, 73 °F	.90 %	ASTM D 570	

→ Resin specification:
ASTM D6778-06 POM0111 superseding ASTM D4181-00 POM100B44330 LD25
Shapes specification:
ASTM D 6100-11 S-POM0111

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Date: 2016/06/27

Version: A0

Distributed by:



Call: 1 (866) 437-7427
Email: info@polymershapes.com
www.polymershapes.com