

TECAMID® 66 MO grey - Stock Shapes

Chemical Designation

PA 66 (Polyamide 66)

Colour

grey

Density

1.14 g/cm³

Fillers

molybdenum disulfide

Main features

- improved surface hardness
- easy to machine
- good mechanical properties
- good tensile strength

Target Industries

- conveyor technology
- heavy duty industry
- power engineering
- mining industry

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	500,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	12,000	psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	@ 73 °F	12,200	psi	ASTM D 638	1) (3) Data from public source
Elongation at yield	@ 73 °F	5	%	ASTM D 638	2)
Elongation at break	@ 73 °F	20	%	ASTM D 638	
Flexural strength	@ 73 °F	19,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	550,000	psi	ASTM D 790	
Compression strength	@1 % strain	1200	psi	ASTM D 695	
Compression strength	@ 10% strain	14000	psi	ASTM D 695	
Compression modulus		292000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.1	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale (R Scale)	84 (119)		ASTM D 785	
Wear rate	Against Steel, 40 psi, 50 fpm	1.9*10 ⁻⁸	in ³ -min/ft-lbs-hr	ASTM D 3702	3)
Thermal properties	condition	value		test method	comment
Melting temperature		491	°F	-	(1) Data from public source
Deflection temperature	@ 66 psi	470	°F	ASTM D 648	1) (2) Data from public source
Deflection temperature	@264 psi	194	°F	ASTM D 648	2) (3) injection molded samples
Service temperature	Long Term	230	°F	-	(4) Data from public source
Service temperature	Intermittent	355	°F	-	
Thermal expansion (CLTE)		4.0*10 ⁻⁵	in/in/°F	ASTM D 696	3)
Specific heat		0.4	BTU/lb-F°	-	4)
Electrical properties	condition	value		test method	comment
surface resistivity		1.0*10 ¹⁴	Ω/square	ASTM D 257	1) (1) Data obtained from public source
Volume resistivity		10 ¹⁵		ASTM D 257	2) (2) Data from public source
Dielectric strength		300	V/mil	ASTM D 149	3) (3) Data from public source
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	2.5		ASTM D 150	4) (4) Data from public source
Other properties	condition	value		test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.40	%	ASTM D 570	
Moisture absorption	@ saturation, 73 °F	7.5 - 8.5	%	ASTM D 570	
Flammability (UL94)		HB		-	

→ Resin specification:
ASTM D6779-11 PA0110L01A00000 and ASTM D4066-01a (Reapproved 2008) PA0110L01A00000
Shapes specification:
ASTM D5989-11 S-PA0121

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.