

**Mitsubishi Chemical Advanced Materials Fluorosint® 500 PTFE, synthetic mica-filled PTFE, compression molded (ASTM Product Data Sheet)**
**Categories:** Polymer; Thermoplastic; Fluoropolymer; Polytetrafluoroethylene (PTFE); Polytetrafluoroethylene (PTFE), Mica Filled

**Material Notes:** Quadrant Engineering Plastic Products is now Mitsubishi Chemical Advanced Materials.

**Key Words:** Polytetrafluoroethylene

Physical Properties	Metric	English	Comments
Specific Gravity	2.32 g/cc	2.32 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.30 %	0.30 %	Immersion; ASTM D570(2)
Deformation	5.0 %	5.0 %	2000 psi; 122°F (50°C)
Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	55	55	ASTM D785
Hardness, Shore D	70	70	ASTM D2240
Tensile Strength	6.89 MPa	1000 psi	ASTM D638
Tensile Strength at 150°C (300°F)	3.45 MPa	500 psi	ASTM D638
Tensile Strength at 65°C (150°F)	6.89 MPa	1000 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Tensile Modulus	2.07 GPa	300 ksi	ASTM D638
Flexural Strength	15.2 MPa	2200 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Compressive Strength	27.6 MPa	4000 psi	10% Def.; ASTM D695
Compressive Modulus	1.72 GPa	250 ksi	ASTM D695
Shear Strength	14.5 MPa	2100 psi	ASTM D732
Izod Impact, Notched	0.481 J/cm	0.900 ft-lb/in	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.15	0.15	Dry vs. Steel; QTM55007
K (wear) Factor	1210 x 10 <sup>-8</sup> mm <sup>3</sup> /N-M	600 x 10 <sup>-10</sup> in <sup>3</sup> -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.280 MPa-m/sec	8000 psi-ft/min	4:1 safety factor; QTM 55007
Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11
Dielectric Constant	2.85 @Frequency 1e+6 Hz	2.85 @Frequency 1e+6 Hz	ASTM D150
Dielectric Strength	10.8 kV/mm	275 kV/in	Short Term; ASTM D149
Dissipation Factor	0.0080 @Frequency 1e+6 Hz	0.0080 @Frequency 1e+6 Hz	ASTM D150
Thermal Properties	Metric	English	Comments
CTE, linear	45.0 µm/m-°C @Temperature -40.0 - 149 °C	25.0 µin/in-°F @Temperature -40.0 - 300 °F	ASTM E831
Thermal Conductivity	0.764 W/m-K	5.30 BTU-in/hr-ft <sup>2</sup> -°F	ASTM F433
Melting Point	327 °C	621 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	260 °C	500 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 3.17 mm	V-0 @Thickness 0.125 in	Estimated Rating
Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	
Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Acceptable	Acceptable	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Unacceptable	Unacceptable	

Alkalies, Weak	Acceptable	Acceptable
Chlorinated Solvents	Acceptable	Acceptable
Conductive / Static Dissipative	No	No
Continuous Sunlight	Acceptable	Acceptable
Hot Water / Steam	Limited	Limited
Hydrocarbons - Aliphatic	Acceptable	Acceptable
Hydrocarbons - Aromatic	Acceptable	Acceptable
Inorganic Salt Solutions	Acceptable	Acceptable
Ketones, Esters	Acceptable	Acceptable

**Descriptive Properties**

Color	Natural	
Machinability	2	1-10, 1=Easier to Machine



Email: [info@polymershapes.com](mailto:info@polymershapes.com)

Call: 1 (866) 437-7427

[www.polymershapes.com](http://www.polymershapes.com)