

Mitsubishi Chemical Advanced Materials TIVAR® 88 ESD UHMW-PE, Premium Glass Filled, Crosslinked Electro Static Dissipative Lining Material (ASTM Product Data Sheet)
Categories: Polymer; Thermoplastic; Polyethylene (PE); High Density (HDPE); High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

Material Notes: Quadrant Engineering Plastic Products is now Mitsubishi Chemical Advanced Materials.

Physical Properties	Metric	English	Comments
Specific Gravity	0.945 g/cc	0.945 g/cc	ASTM D792
Water Absorption	<= 0.01 %	<= 0.01 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	<= 0.01 %	<= 0.01 %	Immersion; ASTM D570(2)

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	67	67	ASTM D2240
Tensile Strength	33.1 MPa	4800 psi	ASTM D638
Tensile Strength at 65°C (150°F)	2.76 MPa	400 psi	ASTM D638
Elongation at Break	250 %	250 %	ASTM D638
Tensile Modulus	0.855 GPa	124 ksi	ASTM D638
Flexural Strength	22.8 MPa	3300 psi	ASTM D790
Flexural Modulus	0.772 GPa	112 ksi	ASTM D790
Compressive Strength	20.7 MPa	3000 psi	10% Def.; ASTM D695
Compressive Modulus	0.600 GPa	87.0 ksi	ASTM D695
Izod Impact, Notched	NB	NB	ASTM D256 Type A
Coefficient of Friction, Dynamic	0.14	0.14	Dry vs. Steel; QTM55007
Sand Slurry	8	8	1018 Steel = 100
Limiting Pressure Velocity	0.140 MPa-m/sec	4000 psi-ft/min	4:1 safety factor; QTM 55007

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	1e+05 - 1.00e+9 ohm	1e+05 - 1.00e+9 ohm	ASTM D257

Thermal Properties	Metric	English	Comments
CTE, linear	180 µm/m-°C @Temperature -40.0 - 149 °C	100 µin/in-°F @Temperature -40.0 - 300 °F	ASTM E831
Melting Point	135 °C	275 °F	Crystalline, Peak; ASTM D3418
Maximum Service Temperature, Air	82.2 °C	180 °F	Long Term
Deflection Temperature at 1.8 MPa (264 psi)	46.7 °C	116 °F	ASTM D648
Flammability, UL94	HB @Thickness 3.17 mm	HB @Thickness 0.125 in	Estimated Rating

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	Yes	Yes	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Unacceptable	Unacceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Limited	Limited	

Descriptive Properties



Email: info@polymershapes.com

Call: 1 (866) 437-7427

www.polymershapes.com